

Eroding Antifouling

General purpose antifouling

PRODUCT DESCRIPTION

Eroding Antifouling is a general purpose antifouling designed to provide good antifouling protection for up to one season. Suitable for all vessel types except for aluminium.

PRODUCT INFORMATION

Product Code	NAU701 - Red, NAU703 - Navy, NAU704 - Black
Typical Shelf Life	2 years
VOC (as supplied)	434 g/ltr
Unit Size	750ml, 2.5lt

DRYING/OVERCOATING INFORMATION

Drying

	5°C (41°F)	15°C (59°F)	23°C (73°F)	35°C (95°F)
Touch Dry	1 hr	45 mins	30 mins	20 mins
Immersion	24 hrs	10 hrs	4 hrs	4 hrs

Note: Max. Immersion Times are as follows: 5-15 °C - 3 mths; 23 °C - 2 mths; 35 °C - 1 mth

Overcoating Ambient / Substrate Temperature

Overcoated By	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
	Min	Max	Min	Max	Min	Max	Min	Max
Eroding Antifouling	16 hrs	Ext	10 hrs	Ext	6 hrs	Ext	4 hrs	Ext

APPLICATION AND USE

Preparation

PREVIOUSLY ANTIFOULED SURFACE

In Good Condition: Rinse with fresh water and allow to dry. If old antifouling is incompatible or unknown, seal with Nautical Underwater Primer.

In Poor Condition: Remove all antifouling then follow priming instructions.

PRIMING For all preparation of unprimed surfaces use Nautical Underwater Primer.

BARE GRP / STEEL / IRON / LEAD / WOOD use Nautical Underwater Primer

Application Methods

Mixing Stir well before use.

Cleaner Nautical NT2

Ventilation and Humidity Control Apply in dry, well ventilated conditions.

Some Important Points

Do not use below 5°C.

Number of Coats

2 coats per season. 3 coats are required on the leading and trailing edges, waterline, rudder and keel.

Eroding Antifouling

General purpose antifouling

Recommended DFT	50 microns dry
Recommended WFT	100 microns wet
Application Methods	Brush, roller
Coverage	(Theoretical) - 10 m ² /lt by brush (Practical) - 9 m ² /lt by brush

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage

GENERAL INFORMATION

Exposure to air and extremes of temperature should be avoided. For the full shelf life of the product to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION

The product should be kept in securely closed containers during transport and storage.

Safety

GENERAL

Read the label safety section for Health and Safety Information.

DISPOSAL

Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. Remainders of this product cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.