

Gloss Enamel

High Gloss Marine Quality Enamel

PRODUCT DESCRIPTION

Nautical Gloss Enamel is a quality one part yacht enamel with good gloss retention. It provides good coverage and a long lasting finish on surfaces above water. The product is easy to apply and is available in 10 bright, attractive colours.

PRODUCT INFORMATION

Product Code	NAU100 – White, NAU101 – Off White, NAU102 – Cream, NAU103 – Yellow, NAU104 – Red, NAU105 – Green, NAU106 – Mid Blue, NAU107 – Dark Blue, NAU108 – Grey, NAU109 – Black
Typical Shelf Life	2 years
VOC (as supplied)	434g/L
Unit Size	750ml, 2.5lt (White only)

DRYING/OVERCOATING INFORMATION

	Drying			
	5°C (41°F)	15°C (59°F)	23°C (73°F)	35°C (95°F)
Touch Dry	6 hrs	3 hrs	2 hrs	1 hrs

	Overcoating Ambient / Substrate Temperature							
	5°C (50°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
	Min	Max	Min	Max	Min	Max	Min	Max
Overcoated By								
Gloss Enamel	24 hrs	4 days	18 hrs	3 days	12 hrs	2 days	8 hrs	2 days

APPLICATION AND USE

Preparation	<p>PREVIOUSLY PAINTED SURFACE:</p> <p>In Good Condition: Wash down with a suitable detergent, rinse with fresh water and allow to dry. Abrade with 280-320 grade (grit) paper.</p> <p>In Poor Condition: Remove all previous coatings and prime the substrate with Nautical Primer & Undercoat.</p> <p>PRIMING: Substrate preparation is covered separately on the primer datasheet.</p>
Application Methods	<p>Mixing Stir well before use.</p> <p>Cleaner Nautical NT1</p> <p>Ventilation and Humidity Control Apply in dry, well ventilated conditions.</p> <p>Spray application - PROFESSIONAL USE ONLY.</p>
Some Important Points	<p>Not suitable for permanently immersed surfaces. Do not use below 5°C.</p> <p>Do not mix Nautical Gloss Enamel and Nautical Primer & Undercoat together.</p>
Number of Coats	3 coats (minimum)
Recommended DFT	38 microns dry
Recommended WFT	75 microns wet



Gloss Enamel

High Gloss Marine Quality Enamel

Application Methods	Brush, roller
Coverage	(Theoretical) - 13.33m ² /lt by brush (Practical) - 12.0m ² /lt by brush

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage

GENERAL INFORMATION

Exposure to air and extremes of temperature should be avoided. For the full shelf life of the product to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION

The product should be kept in securely closed containers during transport and storage.

Safety

GENERAL

Read the label safety section for Health and Safety Information.

DISPOSAL

Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. Remainders of this product cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.