

# Gloss Varnish

High Gloss Marine Quality Varnish

## PRODUCT DESCRIPTION

Gloss Varnish is a traditional, easy to apply, one-part yacht varnish with good gloss retention and flexibility. For use on internal and external wood, especially suited to lighter colour timbers

## PRODUCT INFORMATION

<b>Product Code</b>	NAU200
<b>Typical Shelf Life</b>	2 years
<b>VOC (as supplied)</b>	352 g/ltr
<b>Unit Size</b>	750ml, 2.5lt

## DRYING/OVERCOATING INFORMATION

	Drying			
	5°C (41°F)	15°C (59°F)	23°C (73°F)	35°C (95°F)
Touch Dry	16 hrs	10 hrs	5 hrs	3 hrs

  

	Overcoating Ambient / Substrate Temperature							
	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
	Min	Max	Min	Max	Min	Max	Min	Max
Overcoated By								
Gloss Varnish	36 hrs	5 days	24 hrs	4 days	16 hrs	2 days	12 hrs	1 day

## APPLICATION AND USE

<b>Preparation</b>	<p><b>PREVIOUSLY VARNISHED WOOD:</b>  <b>In Good Condition:</b> Wash down with a suitable detergent, rinse with fresh water and allow to dry. Abrade with 280-320 grade (grit) paper. Remove sanding dust with Nautical NT1.  <b>In Poor Condition:</b> Remove all previous coatings.</p> <p><b>PRIMING BARE WOOD:</b> Thin the first coat by 10-15% with Nautical NT1.</p>
<b>Application Methods</b>	<p><b>Mixing</b> Stir well before use.  <b>Cleaner</b> Nautical NT1  <b>Ventilation and Humidity Control</b> Apply in dry, well ventilated conditions.  <b>Spray application - PROFESSIONAL USE ONLY.</b></p>
<b>Some Important Points</b>	Not suitable for permanently immersed surfaces. Do not use below 5°C.
<b>Number of Coats</b>	3 coats (minimum)
<b>Recommended DFT</b>	40 microns dry
<b>Recommended WFT</b>	77 microns wet

# Gloss Varnish

High Gloss Marine Quality Varnish

---

<b>Application Methods</b>	Brush, roller
<b>Coverage</b>	(Theoretical) - 13.0m <sup>2</sup> /lt by brush (Practical) - 11.7m <sup>2</sup> /lt by brush

## TRANSPORTATION, STORAGE AND SAFETY INFORMATION

### Storage

#### GENERAL INFORMATION

Exposure to air and extremes of temperature should be avoided. For the full shelf life of the product to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.

#### TRANSPORTATION

The product should be kept in securely closed containers during transport and storage.

### Safety

#### GENERAL

Read the label safety section for Health and Safety Information.

#### DISPOSAL

Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. Remainders of this product cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

### IMPORTANT NOTES

*The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.*